

FNRH-609 氯化橡胶防腐面漆(各色)

FNRH-609 Chlorinated Rubber Anticorrosive Finishes

/ HH IN IT	的耐候性					
Very g Characteristics 良好	Very good weather resistance. 良好的耐海水飞溅性和耐油性 Good resistance to oil and seawater spattering. 极好的耐磨性 Very good abrasion resistance. 适用于各种涂装配套 Good compatibility with a wide range of coating systems.					
Good						
Very §						
干燥油	干燥迅速					
Quick	c drying.					
产品用途 主要	用于造船工业及沿海钢结构防腐涂装,亦可用于酸厂、碱厂等大型钢铁设施、储罐外的防					
Uses 腐。						
Used						
facilit	facilities in acid and alkali plant, and for the outside of tanks.					
der 14						
	及各色					
Color White	e and other colors.					
施工条件 无气	喷涂 Airless spray 推荐 Recommended					
Application method 喷嘴力						
压力	Fluid pressure 100~150kg/cm ²					
稀释し	比率 Thinning ratio 0~5% by weight (重量比)					
括用-	适用于常规的喷涂、刷涂和辊涂					
	May be applied by spray, brush, or roller.					
稀释剂 氯化	橡胶稀释剂					
Thinner Chlor	inated rubber thinner					
混合比率 单组织	分					
Mixing ratio One-p						
涂装膜厚 干膜:	干膜: 30μm/道					
Film thickness Dry f	Dry film thickness: 30μm /coat					
固体含量 60%						
Solid content						
比 重 1.2						
Specific gravity						
	值:0.1 千克/平方米/30μm 0.083L/平方米/30μm					
	retical: $0.1 \text{kg/m}^2 / 30 \mu \text{m}$ $0.083 \text{L/m}^2 / 30 \mu \text{m}$					
Coverage rate 实际位	值 : 与表面处理, 外界环境, 施工方法等多种因素有关。					
Actua	al: depending on the surface treatment, environment and application methods.					



干燥时间	温度	10℃	20°C	30℃			
Drying time	Temperature						
	指触干燥	40mins	30mins	20mins			
	Dry to touch						
	实干:	6hrs	5hrs	4hrs			
	Dry to handle:						
	Min. 最小	6hrs	5hrs	4hrs			
涂装间隔	Max. 最大	_	_	_			
Coating interval							
储存期限	一年						
Shelf life	12 months						
包装规格	单组份包装: 20kg/桶						
Packing specification	One-component packing: 2	0 kg/barrel					
-t 11	~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~						
表面处理	底漆表面应清洁干燥,无污物						
Surface preparation	The primer surface must be clean, dry and free of any contaminants.						
	注意施工时与底漆的涂装间隔 Pay attention to the coating interval to the primer during application.						
	ray attention to the coating	g interval to the	primer duri	ig application.			
涂装配套	适用下涂: 氯化橡胶防腐	底漆、氯化橡	胶防腐中层	· 漆或参考我公	司的配套		
Coating system	适用下涂: 氯化橡胶防腐底漆、氯化橡胶防腐中层漆或参考我公司的配套 Preferable preceding coat: Chlorinated Rubber Anticorrosive Primer, Chlorinated F						
2 7	Anticorrosive Intermediate Coat, or refer to our coating system.						
安全注意事项	任何油漆施工中均应保证	提供以下措施	:				
Safety Precautions	The following shall be guaranteed during any paint applications:						
	避免接触皮肤和眼睛。						
	Avoid skin and eye contact.						
	如果油漆接触到皮肤或眼睛,应用大量水冲洗并立即就医。						
	In case of skin or eye contact, flush with large amount of water and immediately get medical						
	attention.						
	保证良好的通风。 Assure well-ventilated working place.						
	小心火灾或爆炸。						
	Take precautions of the risks of fire or explosion.						
	现场遵守一切健康安全规定。						
	Observe all health and safety regulations on site						
提醒注意	本说明书所提供信息均为目前我方所掌握最全面正确的资料,鉴于产品使用条件非我方所能控						
Declaration	制,此中信息不含担保,即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发						
	展,此中所有信息均以我方确认为准。						
	The information given on this technical data sheet is correct to the best of our knowledge. In						
	consideration of the application conditions of the product are beyond our control, so no guarantee is						
	involved herein, namely, we are responsible for the buyers only in terms of their selecting a product.						
	All data must be clarified from our company because of the constantly improvement of our product						
	and its manufacturing proc	CSS.					