

FX-804 过氯乙烯腻子

FX-804 Vinyl Perchloride Putty

产 品 特 性 Characteristics	干燥迅速、填平性好、耐打磨 Fast drying; good dubbing-out property and rubbing resistance.				
产品用途	主要用于填平已喷涂过底漆的金属凹凸表面。				
Uses	Used for dubbing out the primed (by spray) uneven metal surfaces.				
颜 色	灰				
Color	Gray				
施 工 条 件	适用于常规刮涂				
Application	May be applied by doctor blade.				
稀 释 剂 Thinner	专用稀释剂 Special thinner				
混合比率	单组分				
Mixing ratio	Single component				
涂 装 膜 厚	干膜: 0.5mm/道				
Film thickness	Dry film thickness: 0.5mm/coat				
固体含量	80%				
Solid content	80%				
比 重	1.62				
Specific gravity	1.62				
涂 覆 率 Coverage rate	理论值: 0. 63 千克/平方米/0.5mm 0.39 L/平方米/0.5mm				
	Actual: depending on the surface treatment, environment and application methods.				



干燥时间 Drying time	温度(temperature):	20℃	25℃	30°C	
	指触干燥(dry to touch): 实干(dry to handle):	4hrs 72hrs	3hrs 60hrs	2.5hrs 48hrs	
涂装间隔 Coating interval	Min. 最小 Max. 最大	72hrs —	60hrs	48hrs —	
储存期限 Shelf life	一年 12 months				
包装规格 Packing	单组份包装: 20kg/桶 One component package: 20kg/ bucket				
表面处理 Surface preparation	底漆表面应清洁干燥,无污物 Surface of primer should be clean, dry and no contamination				
涂装配套 Coating system	适用底涂: 过氯乙烯底漆 Prime coat: Vinyl Perchloride Primer 适用上涂: 过氯乙烯面漆或参考我公司的配套。 Top coat: Vinyl Perchloride Finish, or refer to our system.				
安全注意事项 Safety Precautions	任何油漆施工中均应保证提供以下措施: The following shall be guaranteed during any paint applications: 避免接触皮肤和眼睛。 Avoid skin and eye contact. 如果油漆接触到皮肤或眼睛,应用大量水冲洗并立即就医。 In case of skin or eye contact, flush with large amount of water and immediately get medical attention. 保证良好的通风。 Assure well-ventilated working place. 小心火灾或爆炸。 Take precautions of the risks of fire or explosion. 现场遵守一切健康安全规定。 Observe all health and safety regulations on site				
提醒注意 Declaration	本说明书所提供信息均为目前我方所掌握最全面正确的资料,鉴于产品使用条件非我方所能控制,此中信息不含担保,即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展,此中所有信息均以我方确认为准。 The information given on this technical data sheet is correct to the best of our knowledge. In consideration of the application conditions of the product are beyond our control, so no guarantee is involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product and its manufacturing process.				

